

MINSEO COATING FLEX CO., LTD.
 382, Jeongmun-ro, Wollong-myeon
 Paju-si, Gyeonggi-do
 Korea


The following sample(s) was/were submitted and identified by/on behalf of the client as:-

SGS File No.	:	AYSA22-06865
Sample Description	:	ONE SAMPLE OF PRINTABLE EP
Color	:	N/A
Style no./Item no.	:	COL-04a, COL-04b
Order No.	:	N/A
Country of Origin	:	N/A
Country of Destination	:	N/A
Proposed care Instruction	:	USING WASHING MACHINE (WATER TEMPERATURE 40 °C, USING DETERGENT WITHOUT SOFTNER) DO NOT IRONING, DO NOT DRY CLEANING, SHADE LINE DRY
Received Date	:	2022. 04. 25
Test Period	:	2022. 04. 25 to 2022. 05. 04
Purpose of Test Report	:	For Self Reference.
Test Method	:	Please refer to next page(s).
Test Results	:	Please refer to next page(s).
Report Comments	:	The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This test report is not related to Korea Laboratory Accreditation Scheme.
Result summary	:	Selected test(s) as requested by client

SGS Korea Co., Ltd.



Daesung Lee / Technical Manager



Test Conducted**Results****Appearance after 5th Washing**

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

Appearance after 10th Washing

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.0..

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

Appearance after 15th Washing

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.0.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

--- Blank ---

Picture of Sample as Received :



AYSA22-06865

*** End of Report ***