

MINSEO COATING FLEX CO., LTD.
 382, Jeongmun-ro, Wollong-myeon
 Paju-si, Gyeonggi-do
 Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as:-

SGS File No. : AYSA22-06877

Sample Description : ONE SAMPLE OF FOAM PU HEAT TRANSFER VINYL

Color : N/A

Style no./Item no. : FM, FMN-SERIES

Order No. : N/A

Country of Origin : N/A

Country of Destination : N/A

Proposed care Instruction : USING WASHING MACHINE (WATER TEMPERATURE 40 °C, USING DETERGENT WITHOUT SOFTENER) DO NOT IRONING, DO NOT DRY CLEANING, SHADE LINE DRY

Received Date : 2022. 04. 25

Test Period : 2022. 04. 25 to 2022. 05. 04

Purpose of Test Report : For Self Reference.

Test Method : Please refer to next page(s).

Test Results : Please refer to next page(s).


Report Comments : The results shown in this test report refer only to the sample(s) tested unless otherwise stated.
 This test report is not related to Korea Laboratory Accreditation Scheme.

Result summary : Selected test(s) as requested by client

SGS Korea Co., Ltd.



Daesung Lee / Technical Manager



Test Conducted**Results****Appearance after 5th Washing**

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

Appearance after 10th Washing

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

Appearance after 15th Washing

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

The surface of the print was noticeably removed.

Therefore, the general appearance of the washed sample is **unsatisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

--- Blank ---

Picture of Sample as Received :



AYSA22-06877

*** End of Report ***

