

**MINSEO COATING FLEX CO., LTD.**  
382, Jeongmun-ro, Wollong-myeon  
Paju-si, Gyeonggi-do  
Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as:-

---

**SGS File No.** : AYSA22-06870

**Sample Description** : ONE SAMPLE OF PEARL PU HEAT TRANSFER VINYL

**Color** : N/A

**Style no./Item no.** : PR SERIES

**Order No.** : N/A

**Country of Origin** : N/A

**Country of Destination** : N/A

**Proposed care Instruction** : USING WASHING MACHINE (WATER TEMPERATURE 40 °C, USING DETERGENT WITHOUT SOFTENER) DO NOT IRONING, DO NOT DRY CLEANING, SHADE LINE DRY

**Received Date** : 2022. 04. 25

**Test Period** : 2022. 04. 25 to 2022. 05. 04

**Purpose of Test Report** : For Self Reference.

**Test Method** : Please refer to next page(s).

**Test Results** : Please refer to next page(s).

**Report Comments** : The results shown in this test report refer only to the sample(s) tested unless otherwise stated.  
This test report is not related to Korea Laboratory Accreditation Scheme.

**Result summary** : Selected test(s) as requested by client

SGS Korea Co., Ltd.



Daesung Lee / Technical Manager

Test Conducted

Results

**Appearance after 5<sup>th</sup> Washing**

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

**Appearance after 10<sup>th</sup> Washing**

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.

The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

**Appearance after 15<sup>th</sup> Washing**

Test Method: Washing Procedure: AATCC 135 -2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry at 25°C, Add 66.0 g of 1993 AATCC Standard Reference Detergent

- Observation on washed sample

No noticeable change was found.

The self-staining of the sample was grade 5.


The color change of the washed sample was grade 4.5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The test was conducted by applicant's request.

--- Blank ---



Picture of Sample as Received :



**AYSA22-06870**

\*\*\* End of Report \*\*\*