

MINSEO COATING FLEX CO., LTD.
382, Jeongmun-ro, Wollong-myeon
Paju-si, Gyeonggi-do
Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as:-

SGS File No. : AYSA21-20843
Sample Description : SUBLI FABRIC
Color : WHITE
Style no./Item no. : N/A
Order No. : N/A
Country of Origin : N/A
Country of Destination : N/A
Proposed care Instruction : MACHINE WASH WATER TEMPERATURE 40 °C, USING DETERGENT WITHOUT SOFTNER, DO NOT IRONING, DO NOT DRY CLEANING, SHADE LINE DRY
Received Date : 2021. 12. 20
Test Period : 2021. 12. 20 to 2021. 12. 28
Purpose of Test Report : For Self Reference.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).
Report Comments : The results shown in this test report refer only to the sample(s) tested unless otherwise stated.
This test report is not related to Korea Laboratory Accreditation Scheme.
Result summary : Selected test(s) as requested by client

SGS Korea Co., Ltd.



Daesung Lee / Technical Manager

Test Conducted

Results

Appearance after 5th Washing

Test Method: Washing Procedure: AATCC 150-2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry, Add 66.0 g of 1993 AATCC Standard Reference Detergent
 - Observation on washed sample

The color of the sample was almost the same as that of the original state (grade 4.5).
 The seams were not frayed or opened.
 The stitches were not broken.
 Fuzzing and pilling on the fabric was not occurred.
 No noticeable shape distortion was found.
 The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.
 The test was conducted by applicant's request.

Appearance after 10th Washing

Test Method: Washing Procedure: AATCC 150-2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry, Add 66.0 g of 1993 AATCC Standard Reference Detergent
 - Observation on washed sample

The color of the sample was almost the same as that of the original state (grade 4.5).
 The seams were not frayed or opened.
 The stitches were not broken.
 Fuzzing and pilling on the fabric was not occurred.
 No noticeable shape distortion was found.
 The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.
 The test was conducted by applicant's request.


Appearance after 15th Washing

Test Method: Washing Procedure: AATCC 150-2018t: Machine wash at (41 ± 3) °C with 1.8 kg dummy loading, Normal cycle, Line dry, Add 66.0 g of 1993 AATCC Standard Reference Detergent
 - Observation on washed sample

The color of the sample was almost the same as that of the original state (grade 4.5).
 The seams were not frayed or opened.
 The stitches were not broken.
 Fuzzing and pilling on the fabric was not occurred.
 No noticeable shape distortion was found.
 The self-staining of the sample was grade 5.

Therefore, the general appearance of the washed sample is **satisfactory**.

<Note> Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.
 The test was conducted by applicant's request.



Picture of Sample as Received :



AYSA21-20843

*** End of Report ***